

Dist: A

AD-A284 102

ATION PAGE



ATE

3. REPORT TYPE AND DATES COVERED

ANNUAL 01 Feb 93 TO 31 Jan 94

4. TITLE AND SUBTITLE

ELEMENTAL FLUORINE BASED SYNTHESIS OF PENTAFLUORO
PHENYL AND OTHER AROMATIC PERFLUOROPOLYETHER POLYMERS

F49620-92-J-0104

61102F

6. AUTHOR(S)

Dr Richard J. Lagow

2303

DS


7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

University of Texas at Austin
Dept of Chemistry
Austin TX 78712-1167

AFOSR-TR- 94 05 11'

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Dr Frederick L. Hedberg
AFOSR/NL
110 Duncan Ave Suite B115
Bolling AFB DC 20332-0001



11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION AVAILABILITY STATEMENT

Approved for public release;
distribution unlimited.

A

13. ABSTRACT (Maximum 200 words)

Since we successfully obtained a fused perfluoro (benzofuran) from perfluoro (dicyclohexyl ether), reductive defluorination of the perfluorinated ethers containing three perfluoro (cyclohexyl) groups would be interesting. The three isomers of o-, m-, and p- perfluoro (dicyclohexanoxyl cyclohexane) were prepared by liquid-phase direct fluorination of o-, m-, and p- diphenoxyl benzene. After several runs of liquid-phase direct fluorination, enough amount of o-perfluoro (dicyclohexanoxyl cyclohexane) was collected to carry out the following reductive defluorination. The reductive defluorination was carried out from -70 to 70 degree for 2 days, but the ortho-ether, however, kept unreacted. One of the reasons for that is perhaps steric hindrance. Reductive defluorination of the meta- and para- ethers are under investigation.

DTIC QUALITY INSPECTED 3

14. SUBJECT TERMS

15. NUMBER OF PAGES

16. PRICE CODE

17. SECURITY CLASSIFICATION OF REPORT

(U)

18. SECURITY CLASSIFICATION OF THIS PAGE

(U)

19. SECURITY CLASSIFICATION OF ABSTRACT

(U)

20. LIMITATION OF ABSTRACT

(U)

GENERAL INSTRUCTIONS FOR COMPLETING SF 298

The Report Documentation Page (RDP) is used in announcing and cataloging reports. It is important that this information be consistent with the rest of the report, particularly the cover and title page. Instructions for filling in each block of the form follow. It is important to **stay within the lines to meet optical scanning requirements.**

Block 1. Agency Use Only (Leave Blank)

Block 2. Report Date. Full publication date including day, month, and year, if available (e.g. 1 Jan 88). Must cite at least the year.

Block 3. Type of Report and Dates Covered. State whether report is interim, final, etc. If applicable, enter inclusive report dates (e.g. 10 Jun 87 - 30 Jun 88).

Block 4. Title and Subtitle. A title is taken from the part of the report that provides the most meaningful and complete information. When a report is prepared in more than one volume, repeat the primary title, add volume number, and include subtitle for the specific volume. On classified documents enter the title classification in parentheses.

Block 5. Funding Numbers. To include contract and grant numbers; may include program element number(s), project number(s), task number(s), and work unit number(s). Use the following labels:

C - Contract	PR - Project
G - Grant	TA - Task
PE - Program Element	WU - Work Unit Accession No.

Block 6. Author(s). Name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. If editor or compiler, this should follow the name(s).

Block 7. Performing Organization Name(s) and Address(es). Self-explanatory.

Block 8. Performing Organization Report Number. Enter the unique alphanumeric report number(s) assigned by the organization performing the report.

Block 9. Sponsoring/Monitoring Agency Names(s) and Address(es). Self-explanatory.

Block 10. Sponsoring/Monitoring Agency Report Number. (If known)

Block 11. Supplementary Notes. Enter information not included elsewhere such as: Prepared in cooperation with...; Trans. of ..., To be published in When a report is revised, include a statement whether the new report supersedes or supplements the older report.

Block 12a. Distribution/Availability Statement. Denote public availability or limitation. Cite any availability to the public. Enter additional limitations or special markings in all capitals (e.g. NOFORN, REL, ITAR)

DOD - See DoDD 5230.24, "Distribution Statements on Technical Documents."

DOE - See authorities

NASA - See Handbook NHB 2200.2.

NTIS - Leave blank.

Block 12b. Distribution Code.

DOD - DOD - Leave blank

DOE - DOE - Enter DOE distribution categories from the Standard Distribution for Unclassified Scientific and Technical Reports

NASA - NASA - Leave blank

NTIS - NTIS - Leave blank.

Block 13. Abstract. Include a brief (Maximum 200 words) factual summary of the most significant information contained in the report.

Block 14. Subject Terms. Keywords or phrases identifying major subjects in the report.

Block 15. Number of Pages. Enter the total number of pages.

Block 16. Price Code. Enter appropriate price code (NTIS only).

Blocks 17. - 19. Security Classifications. Self-explanatory. Enter U.S. Security Classification in accordance with U.S. Security Regulations (i.e., UNCLASSIFIED). If form contains classified information, stamp classification on the top and bottom of the page.

Block 20. Limitation of Abstract. This block must be completed to assign a limitation to the abstract. Enter either UL (unlimited) or SAR (same as report). An entry in this block is necessary if the abstract is to be limited. If blank, the abstract is assumed to be unlimited.

Second Annual Technical Report

to

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH

Washington, DC 20332

ELEMENTAL FLUORINE BASED SYNTHESSES OF PENTAFLUORO PHENYL
AND OTHER AROMATIC PERFLUOROPOLYETHER POLYMERS

Grant Number F49620-92-J-0104

February 1, 1993 - January 31, 1994

Presented by

Professor Richard J. Lagow

Department of Chemistry

The University of Texas at Austin

Austin, Texas 78712

TEL (512) 471-1032

FAX (512) 471-8648

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

QUALITY INSPECTED 8


94-29000




318

94 9 06 07 9



In last annual technical report, reductive defluorination of perfluoro(dicyclohexylether) was carried out with sodium benzophenone and the two perfluoro(cyclohexyl) groups were interestingly fused to form perfluoro(bezofuran). What about other perfluoro(dicyclohexyl) compounds ? Will they form fused products or other interesting compounds after the reductive defluorination ?




Perfluoro(dicyclohexyl) was prepared in 91% yield by liquid-phase direct fluorination of dicyclohexyl. Reductive defluorination of the perfluorinated compound produced a nonfused product, perfluoro(diphenyl), other than a fused product.



311 . 002 MJB 06MAY94
JNG, CFCL3, CDCL3, F19



File: LAGO1827 Ident: 10 12 SMO(1,5) PKD(5,3,5,0.20%,0.0,20.00%,F,F) SPEC (Height, Centroid) Acq: 29-APR-1994 17:03:20 42110 CALIBRAGO1827
 AB-E CI+ Voltage Bp1: 9455616 TIC: 169071248 Flags: NORM
 File Text: 50PMOLE/UL/5UL/MIN



Elemental Composition

Date: 29-APR-1994



File: LAGO1827 Ident: 10 12 SMO(1,5) PKD(5,3,5,0.20%,0.0,20.00%,F,F)
 2AB-E CI+ Voltage Bp1: 9455616 TIC: 169071248 Flags: NORM
 File Text: 50PMOLE/UL/5UL/MIN

Heteroatom Max: 20 Ion: Both Even and Odd
 Limits:


Mass	333.900	0.0	-10.0	U	0	0
	334.000	100.0	80.0	200	400	10
Mass	333.984532	100.0	-0.5	-1.5	333.984033	8.0
						12
						10

M⁺


Perfluoro(dicyclohexyl) ketone was prepared in 82% yield by liquid-phase direct fluorination of dicyclohexyl ketone. Reductive defluorination of the perfluorinated ketone is under investigation.





3111 002 MJB 13MAY94
 ING, CFCL3, CDCL3, F19, 20C



ONE-PULSE SEQUENCE
 P2= 8.00 USEC
 D5= 1.00 SEC
 NA = 104
 SIZE = 32768
 AT = 212.99 MSEC
 QPD ON = 4
 ABC ON
 BUTTERWORTH FILTER ON
 DB ATT. = 3
 ADC = 12 BITS
 AI = 8
 SW = +/- 38461.5
 DW = 13
 RG = 10 USEC
 DE = 13 USEC
 TL HIGH POWER ON
 F2 = 361.084524
 BB MODULATION ON
 OF = -34144.68
 SF = 339.723167
 EM = 3.00
 PA = 227.8
 PB = 32.0
 T(C) = -10
 SCALE = 1868.61 HZ/CM
 = 5.5004 PPM/CM



File: LAG01776 Ident: 1 SMO(1,5) BSUB(128,15,-3.0) PKO(5,3,5,0.05%,1356.0,50.00%,F,F) SPEC(Haights, Centroid) Acq: 27-APR-1994 13:48:19 +0:15
 AB-E CI+ Voltage Bp1: 620288 TIC: 33926488 Flags: NORM
 File Text: ISOBUTANE/LJ



Date: 27-APR-1994



Elemental Composition

File: LAG01776 Ident: 1 SMO(1,5) BSUB(128,15,-3.0)
 ZAB-E CI+ Voltage Bp1: 620288 TIC: 33926488 Flags: NORM
 File Text: ISOBUTANE/LJ


Heteroatom Max:		30	Ion:		Both Even and Odd					
Limits:										
590.900	0.0					-10.0	0	0	0	22
590.980	100.0	2.0				80.0	200	400	1	22
Mass	%RA	mDa	PPM	Calcd. Mass	DBE	C	H	O	F	
590.966110	39.4	1.5	2.5	590.967611	2.5	13	1	1	1	22

(M+H)⁺

Since we successfully obtained a fused perfluoro(benzofuran) from perfluoro(dicyclohexyl ether), reductive defluorination of the perfluorinated ethers containing three perfluoro(cyclohexyl) groups would be interesting. The three isomers of o-, m-, and p-perfluoro(dicyclohexanoxyl cyclohexane) were prepared by liquid-phase direct fluorination of o-, m-, and p- diphenoxyl benzene. After several run of liquid-phase direct fluorination, enough amount of o-perfluoro(dicyclohexanoxyl cyclohexane) was collected to carry out the following reductive defluorination. The reductive defluorination was carried out from -70 to 70 °C for 2 days, but the ortho-ether, however, kept unreacted. One of the reasons for that is perhaps steric hindrance. Reductive defluorination of the meta- and para- ethers are under investigation.




S222 . 004 MJB 11MAR94
 UNG, CDCL3, F19, -30




ONE-PULSE SEQUENCE

P2= 8.00 USEC
 D5= 1.00 SEC
 NA = 104
 SIZE = 32768
 AT = 163.84 MSEC
 OPD ON = 4
 ABC ON
 BUTTERWORTH FILTER ON
 DB ATT = 3
 ADC = 12 BITS
 AI = 5
 SW = +/- 50000.0
 DW = 10
 RG = 10 USEC
 DE = 10 USEC
 TL HIGH POWER ON
 F2= 361.084524
 BB MODULATION ON
 OF = -18096.17
 SF = 339.739179
 EM = 3.00
 PA = 270.3
 PB = 33.0
 T(C) = -30
 SCALE = 1528.93 HZ/CM
 = 4.5003 PPM/CM



File: LAG00866 Ident: 18 20 SMO(1,3) PKD(5,3,5,0.05%,0.0,50.00%,F,F) LSEC(Brighten, Centroid) Acq: 9-MAR-1994 16:49:36 13:30 Cal: LAG00866
 SAB-E CI+ Voltage Bp1: 392352 TIC: 86608752 Flags: NORM DEL
 File Text: isobutane/1j




Elemental Composition Date: 9-MAR-1994


File: LAG00866 Ident: 18 20 SMO(1,3) PKD(5,3,5,0.05%,0.0,50.00%,F,F)
 SAB-E CI+ Voltage Bp1: 392352 TIC: 86608752 Flags: NORM DEL
 File Text: isobutane/1j
 Heteroatom Max: 40 Ion: Both Even and Odd

Mass	836.940	0.0	-10.0	0	0	0	30
	836.950	100.0	80.0	200	400	2	32
Mass	836.942242	100.0	-1.9	-2.3	836.940330	3.5	18
Mass	836.942242	100.0	-1.9	-2.3	836.940330	3.5	18
Mass	836.942242	100.0	-1.9	-2.3	836.940330	3.5	18

(M-F)⁺




00 . 004 MJB 24NOV93
 IG, CDCL3, CFCL3, F19, -30



ONE-PULSE SEQUENCE

P2= 8.00 USEC
 D5= 1.00 SEC
 NA = 208
 SIZE = 32768
 AT = 163.84 MSEC
 QPD ON = 4
 ABC ON
 BUTTERWORTH FILTER ON
 DB ATT.= 3
 ADC = 12 BITS
 AI = 4
 SW = +/- 50000.0
 DW = 10
 RG = 10 USEC
 DE = 10 USEC
 TL HIGH POWER ON
 F2 = 361.084524
 QD MODULATION ON
 OF = -18106.64
 SF = 339.739179
 EM = 3.00
 PA = 349.2
 PB = 23.6
 T(C) = -30
 SCALE = 1359.25 HZ/CM
 = 4.0008 PPM/CM



854.947

PRK

Elemental Composition

Date 21-JAN-1994

File:LAC0044 Ident:1 3 SMO(1,5) PKD(5,3,5,0.05%,0.0,40.00%,F,T)
ZAB-E Cit Voltage BPI:1669344 TIC:108087816 Flags:NORM
File Text:ISOBUTANE/LJ

Ion: Both Even and Odd
Neteroatom Max: 40
Limits:

055.900	1.0
056.000	100.0
	2.0

Mass GRA mDa
055.939342 15.4 -0.6

DBE	C	H	O	F
-10.0	0	0	0	0
80.0	200	400	2	32

$$M^+$$

855.939

856.954


057.362

875


956

857,

2/11



3200 . 002 MJB 06JAN94
JNG, CDCL3, CFCL3, F19




ONE-PULSE SEQUENCE

P2= 8.00 USEC
D5= 1.00 SEC
NA = 104
SIZE = 32768
AT = 163.84 MSEC
OPD ON = 4
ABC ON
BUTTERWORTH FILTER ON
DB ATT. = 3
ADC = 12 BITS
AI = 2
SW = +/- 50000.0
DW = 10
RG = 10 USEC
DE = 10 USEC
TL HIGH POWER ON
F2 = 361.084524
BD MODULATION ON
OF = -18012.39
SF = 339.739179
EM = 1.00
PA = 262.0
PB = 39.0
T(C) = -20
SCALE = 1359.25 HZ/CM
= 4.0008 PPM/CM

4
4
4

Mass	IR	ND	PPH	Calcd. Mass	DBE	C	H	O	F
836.935065	100.0	5.3	6.3	836.940330	3.5	18	2	2	31

 $(M-F)^+$ 

Synthesis of perfluoro(hexamethylcyclohexane-1,3,5-trione) was reported in last report. Now we want to show its unusual solid state conformation. The molecule is unusually flattened, as can be seen from the sum of the six ring torsion angles $31 + 18 + 14 + 32 + 18 + 12 = 125^\circ$. By contrast, the sum of the ring torsional angles in cyclohexane and hexamethylcyclohexane-1,3,5-trione are 336 and 192° , respectively. In comparison with boat conformation of hexamethylcyclohexane-1,3,5-trione, conformation of the perfluorinated analogue is a twisted boat in order to avoid the three axial trifluoromethyl groups, coming much too close and creating a serious strain.





Fig.1. Molecular structure of $C_{12}F_{18}O_3$ (1).;


Selected bond lengths (Å): C(2)-O(2) 1.188(5), C(4)-O(4) 1.179(5), C(6)-O(6) 1.178(5); bond angles (°): C(2)-C(1)-C(6) 115.7(4), C(2)-C(3)-C(4) 115.8(4), C(6)-C(5)-C(4) 116.0(4); torsion angles (°): C(6)-C(1)-C(2)-C(3) -30.8(6), C(1)-C(2)-C(3)-C(4) 17.9(6), C(2)-C(3)-C(4)-C(5) 14.4(6), C(3)-C(4)-C(5)-C(6) -32.3(6), C(4)-C(5)-C(6)-C(1) 18.3(6), C(2)-C(1)-C(6)-C(5) 11.8(6).

Other homologs of diphenyl ether such as 1,3-, and 1,4- diphenoxy benzene have also been perfluorinated for subsequent reductive defluorination.




Chemical Ionization MS

Parent	-	872
P-F	-	853
P- (C ₆ F ₁₁)	-	591
P- (C ₆ F ₁₁ O)	-	575
P- (C ₆ F ₁₁ O-C ₆ F ₁₀)	-	297
P- 2x (C ₆ F ₁₁ O)	-	278




We have done considerable work on defluorination of cyclohexyl substituted fluorine compounds. This work is now becoming more and more successful and has been aided very considerably by the publication of a full manuscript by Dr. Guido Pez on methods using sodium benzophenone (J. Org. Chem. 1992, 57, 2856-2860). Yet removing extra fluorines remains one of the problems that we are in the process of solving. There are a series of sodium substituted defluorination reagents. One of the mildest is sodium phenylthiolate by Professor David McNicol of Glasgow. The synthesis of perfluoro biscyclohexyl ether was accomplished in 83% yield.



The ^{19}F NMR Spectrum of Biscyclohexyl Ether


5051 004 MJB
JNG. CDCL3. CFCL3.
19. -30DEG


20OCT93




ONE-PULSE SEQUENCE
P2= 8.00 USEC
DS= 1.00 SEC
NA = 104
SIZE = 32768
AT = 163.84 USEC
GPD ON = 4
ADC ON
BUTTERWORTH FILTER ON
DB ATT = 3
ADC = 12.8175
AZ = 1
SW = +/- 50000.0
BW = 10
RG = 10 USEC
SC = 10 USEC
TL HIGH POWER ON
F2= 361.004524
BB MODULATION ON
QF = -18103.62
SF = 336.720170
EPR = 3.00
PAM = 337.5
PDM = 43.4
T(C) = -25
SCALE = 1350.25 Hz/CH
4.0000 PPM/C

The high resolution mass spectrum of the final product contains a parent peak at 577.9588.






¹⁹F NMR Spectrum of the Defluorinated Product



This is a very interesting case. Two extra fluorine were removed and we obtained the very interesting perfluoro furan compound shown above. We are now think we have been successful in applying it to a four-membered perfluoro cyclohexyl ether (page 7) (degree of polymerization four) and we shall see if we get the furan structure on that one as well. If successful it should produce an oligomer containing three furan units.

Preparation of Perfluorinated Salicylic Acid



By first synthesizing in 60% yield the perfluoro aromatic precursor, namely 1-hydroxy-2-fluorobenzene, we then synthesized 2,3,4,5-tetrafluoro-6-hydroxybenzoic acid by the following procedure:




This step resulted in perfluorinated salicylic acid in 90% yield. Esters of salicylic acid are currently the most widely used lubrication antifriction additives to motor oils. We are now experimenting with making substituted hydrocarbon ester tails with one chlorine to make the product more soluble in polyalphaolefins and petroleum oils.

The ^{19}F NMR Spectrum of Perfluoro Salicylic Acid


S060 . 002 MJB 22JUL93
JNG, D6-ACETONE, CFCL3



Very unusual perfluoro polyketone structures have been prepared by Dr. Kuangsen Sung. In particular, Dr. Sung has prepared a perfluorinated ketone from a hydrocarbon starting material in 72% yield.





We have also obtained the crystal structure of this unusual new fluorocarbon material.



The ^{19}F NMR Spectrum of the Perfluorinated Ketone

SD70A. 002 BAS 25AUG93
JN3. ACETONE-D6, CFCL3, F19




ONE-PULSE SEQUENCE

P2= 8.00 USEC
DS= 1.00 SEC

NA = 104
SIZE = 32768
AT = 163.84 MSEC
QPD ON = 4
ABC ON
BUTTERWORTH FILTER ON
DB ATT. = 3
ADC = 12 BITS
AI = 1
SW = +/- 50000.0
DSW = 10
RG = 10 USEC
DE = 10 USEC
TL HIGH POWER ON
F2 = 341.084524
BB MODULATION ON
CF = -17654.26
SF = 339.739179
EM = 3.00
PA = 159.1
PB = 54.8



SCALE 5000.00 HZ/CM
= 14.7171 PPM/CM

C12 F18 03





We think the zeolitic solid state structure of this very interesting perfluoro polyketone is most unusual and there may be interesting chemistry associated with the pockets of such a material.

Zeolitic Structure of




A number of other perfluoro organometallic compounds have been prepared for their conversion to perfluoro aromatic analogs.





F

This structure is very interesting for under certain circumstances we hope to get the furan structure and with other reagents we hope to get the perfluorinated phenyl material. The perfluorinated cyclohexyl analog is already in hand.


<u>+/- C.I. Fragment</u>	<u>m/e</u>
P - F	1115
P - C ₆ F ₁₁	853
P - OC ₆ F ₁₁	837
P - C ₆ F ₁₀ OC ₆ F ₁₁	575
P - OC ₆ F ₁₀ OC ₆ F ₁₁	559




<u>+/- C.I. Fragment</u>	<u>m/e</u>
Parent minus F	1381
P - C ₆ F ₁₁	1119
P - OC ₆ F ₁₁	1103
P - CF ₂ -O-C ₆ F ₁₁	1053




Mr. Han-Chao Wei of our research program has fluorinated this interesting crown ether polymer. We are very interested in exploring the defluorination process to see if we obtain the defluorinated material as indicated in the proposed structure.




↓
F₂/He
NaF/CCl₄



? ↓ defluorination process



He(cm ³ /min.)	F ₂ (cm ³ /min.)	Time(hr.)
50	0	0.5
50	2	24
25	2	24
10	3	24
3	3	24
0	3	24
25	0	0.5



Elemental analyses of the Perfluoro-crown ether-polymer

	<u>Found</u>	<u>Calculated</u>
Carbon —	24.38% 24.34%	24.92%
Fluorine —	64.68% 64.59%	65.11%
Oxygen —	----	9.97%

***Elemental analyses were done by Schwarzkopf Microanalytical Laboratory
in New York**